

LEXAN™ COPOLYMER ML6411

REGION EUROPE

DESCRIPTION

LEXAN ML6411 polycarbonate (PC) siloxane resin, is a high flow opaque injection molding (IM) grade with very low temperature ductility characteristics. This grade offers UL94 V0 @ 1.5mm and 5VA @ 3.0mm flame retardancy based on non-chlorine, non-bromine FR systems. LEXAN ML6411 resin offers excellent processing characteristics with opportunity for shorter IM cycle times compared to standard PC. This product is available in a wide range of opaque colors and is an excellent candidate for a wide range of electrical applications.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2600	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	62	MPa	ISO 527
Tensile Stress, break, 50 mm/min	58	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	100	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2350	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	900	J/m	ASTM D 256
Izod Impact, notched, -30°C	150	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	72	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	60	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	15	kJ/m ²	ISO 180/1A
THERMAL			
Vicat Softening Temp, Rate B/50	134	°C	ASTM D 1525

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	114	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	128	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	119	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.7E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.9E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	134	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	125	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	115	°C	ISO 75/Ae
Relative Temp Index, Elec	100	°C	UL 746B
Relative Temp Index, Mech w/impact	100	°C	UL 746B
Relative Temp Index, Mech w/o impact	100	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	7	g/10 min	ASTM D 1238
Melt Flow Rate, 300°C/1.2 kgf	15	g/10 min	ASTM D 1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.3	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 260°C/5.0 kg	18	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	26.5	kV/mm	ASTM D 149
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Comparative Tracking Index	250	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94-5VA Rating (3)(4)	3	mm	UL 94 by SABIC-IP
UL Recognized, 94V-0 Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94-5VA Rating (3)	3	mm	UL 94
UL Recognized, 94-5VB Rating (3)	2	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	800	°C	IEC 60695-2-13

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Glow Wire Ignitability Temperature, 2.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 300	°C	
Nozzle Temperature	250 – 290	°C	
Front - Zone 3 Temperature	260 – 300	°C	
Middle - Zone 2 Temperature	250 – 290	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.