

# LNP™ THERMOCOMP™ COMPOUND DX06413H

DF-1008 EM MR BE  
REGION AMERICAS

## DESCRIPTION

LNP THERMOCOMP DX06413H is a compound based on Polycarbonate resin containing 40% Glass Fiber. Added features of this material include: Easy Molding, Mold Release.

## TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, break	84	MPa	ASTM D 638
Tensile Strain, break	1.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	10540	MPa	ASTM D 638
Flexural Stress	117	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	373	J/m	ASTM D 4812
Izod Impact, notched, 23°C	53	J/m	ASTM D 256
<b>MECHANICAL PROPERTIES</b>			
Flexural modulus	11030	MPa	ISO 178/1A
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.