

CYCOLOY™ FR RESIN CX7240

REGION ASIA

DESCRIPTION

CYCOLOY CX7240 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) resin is an enhanced performance & processability grade that can be injection molded. This non-chlorinated, non-brominated flame retardant PC/ABS has a UL V0 & 5VA/B flame rating. CYCOLOY CX7240 resin is an excellent candidate for a wide variety of thin wall applications including enclosures.

TYPICAL PROPERTY VALUES

Revision 20180226

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.1	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	2600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	104	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2500	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	96	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	700	J/m	ASTM D 256
Izod Impact, notched, -30°C	175	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	65	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	20	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	22	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	110	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	100	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	89	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	99	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	110	°C	ISO 306
Vicat Softening Temp, Rate B/120	113	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	93	°C	ISO 75/Af
Relative Temp Index, Elec	90	°C	UL 746B
Relative Temp Index, Mech w/impact	90	°C	UL 746B
Relative Temp Index, Mech w/o impact	90	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	18	g/10 min	ASTM D 1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	15	cm ³ /10 min	ISO 1133
ELECTRICAL			
Hot Wire Ignition {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
FLAME CHARACTERISTICS			
UL Recognized, 94V-1 Flame Class Rating (3)	0.6	mm	UL 94

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94V-0 Flame Class Rating (3)	0.75	mm	UL 94
UL Recognized, 94-5VA Rating (3)	3	mm	UL 94
UL Recognized, 94-5VB Rating (3)	1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	0.75	mm	IEC 60695-2-12
Glow Wire Flammability Index 960°C, passes at, by VDE	0.75	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 0.75 mm, by VDE	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm, by VDE	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm, by VDE	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	34	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 300	°C	
Nozzle Temperature	250 – 300	°C	
Front - Zone 3 Temperature	250 – 300	°C	
Middle - Zone 2 Temperature	240 – 290	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 85	°C	
Vent Depth	0.03 - 0.075	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.