

ULTEM™ RESIN 1000FC

REGION EUROPE

DESCRIPTION

ULTEM 1000FC resin is an amorphous, transparent polyetherimide (PEI) plastic offering a glass transition temperature (T_g) of 217°C. This inherently flame retardant resin has UL94 V0, V2 and 5VA ratings and is RoHS compliant. ULTEM 1000FC resin is an unreinforced general purpose grade offering high heat resistance, high strength and modulus and broad chemical resistance up to high temperatures. This grade is US FDA and EU Food Contact compliant and has NSF51 listing for selected colors.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	105	MPa	ISO 527
Tensile Stress, break, 50 mm/min	85	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	60	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	160	MPa	ISO 178
Flexural Modulus, 2 mm/min	3300	MPa	ISO 178
Hardness, H358/30	140	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	10	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m ²	ISO 179/1eA
THERMAL			
Thermal Conductivity	0.24	W/m-°C	ISO 8302
CTE, 23°C to 150°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	5.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate A/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/50	211	°C	ISO 306
Vicat Softening Temp, Rate B/120	215	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	200	°C	ISO 75/Be

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	190	°C	ISO 75/Ae
Relative Temp Index, Elec	170	°C	UL 746B
Relative Temp Index, Mech w/impact	170	°C	UL 746B
Relative Temp Index, Mech w/o impact	170	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow (2) (5)	0.5 – 0.7	%	SABIC method
Density	1.27	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	1.25	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	13	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0005	-	IEC 60250
Dissipation Factor, 1 MHz	0.006	-	IEC 60250
Dissipation Factor, 2450 MHz	0.0025	-	IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Comparative Tracking Index, M	100	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating (3)	0.4	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating (3)	0.75	mm	UL 94
UL Recognized, 94-5VA Rating (3)	3	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	3.2	mm	IEC 60695-2-12
Oxygen Index (LOI)	47	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	370 – 410	°C	
Nozzle Temperature	350 – 405	°C	
Front - Zone 3 Temperature	360 – 415	°C	
Middle - Zone 2 Temperature	350 – 405	°C	
Rear - Zone 1 Temperature	340 – 395	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.