

# DuPont™ Crastin® FG6129 NC010

## THERMOPLASTIC POLYESTER RESIN

Product Information

Crastin® FG6129 NC010 is an unreinforced, high viscosity polybutylene terephthalate resin for extrusion and injection moulding. It has been developed for consideration into applications such as parts for the food industry.

**FOOD CONTACT**

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from your DuPont representative.

General information	Value	Unit	Test Standard
Resin Identification	PBT	-	ISO 1043
Part Marking Code	PBT	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Melt mass-flow rate	10	g/10min	ISO 1133
Melt mass-flow rate, Temperature	250	°C	ISO 1133
Melt mass-flow rate, Load	2.16	kg	ISO 1133
Viscosity number	150	cm <sup>3</sup> /g	ISO 307, 1157, 1628
Moulding shrinkage, parallel	1.7	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.5	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	2600	MPa	ISO 527-1/-2
Yield stress	58	MPa	ISO 527-1/-2
Yield strain	5	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Strain at Break, 23°C, 50mm/min	200	%	ISO 527-1/-2
Flexural Modulus	2350	MPa	ISO 178
Flexural Strength	85	MPa	ISO 178
Poisson's ratio	0.38	-	ISO 527-1/-2
Tensile creep modulus			ISO 899-1
1h	2600	MPa	
1000h	1800	MPa	
Charpy impact strength			ISO 179/1eU
23°C	N	kJ/m <sup>2</sup>	
-30°C	N	kJ/m <sup>2</sup>	
Charpy notched impact strength			ISO 179/1eA
23°C	5.5	kJ/m <sup>2</sup>	
-30°C	4	kJ/m <sup>2</sup>	
Izod notched impact strength			ISO 180/1A
23°C	4.5	kJ/m <sup>2</sup>	
-30°C	6	kJ/m <sup>2</sup>	
Izod impact strength			ISO 180/1U
23°C	N	kJ/m <sup>2</sup>	
-30°C	130	kJ/m <sup>2</sup>	
Ball indentation hardness, H 961/30	139	MPa	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load			ISO 75-1/-2
1.8 MPa	50	°C	
0.45 MPa	115	°C	
0.45 MPa, annealed	180	°C	
1.8 MPa, annealed	60	°C	

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

**North America**

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

**Asia Pacific**

Tel: +81 3 5521 8600

**Europe/Middle East/Africa**

Tel: +41 22 717 51 11



# DuPont™ Crastin® FG6129 NC010

## THERMOPLASTIC POLYESTER RESIN

Vicat softening temperature			ISO 306
50 °C/h, 50N	175	°C	
50 °C/h, 10N	215	°C	
Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion			ISO 11359-1/-2
normal	130	E-6/K	
Normal, -40-23 °C	0.9	E-6/K	
Normal, 55-160 °C	1.6	E-6/K	
Parallel, -40-23 °C	0.7	E-6/K	
Parallel, 55-160 °C	1.8	E-6/K	
Thermal conductivity of melt	0.25	W/(m K)	-
Spec. heat capacity of melt	2090	J/(kg K)	-
RTI, electrical			UL 746B
1.5mm	75	°C	
3mm	75	°C	
RTI, impact			UL 746B
1.5mm	75	°C	
3mm	75	°C	
RTI, strength			UL 746B
1.5mm	75	°C	
3mm	75	°C	
<b>Flammability</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Burning Behav. at 1.5mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	UL	-	UL 94
Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.9	mm	IEC 60695-11-10
UL recognition	UL	-	UL 94
Oxygen index	22	%	ISO 4589-1/-2
Glow Wire Flammability Index			IEC 60695-2-12
1.5mm	960	°C	
3mm	850	°C	
Hot Wire Ignition			UL 746A
1.5mm	15	s	
3mm	30	s	
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<100	mm/min	ISO 3795 (FMVSS 302)
<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E12	Ohm	IEC 62631-3-2
Electric strength	26	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption, 2mm	0.2	%	Sim. to ISO 62
Water absorption, 2mm	0.4	%	Sim. to ISO 62
Density	1300	kg/m <sup>3</sup>	ISO 1183
Density of melt	1120	kg/m <sup>3</sup>	-
<b>Injection</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Recommended	yes	-	-
Drying Temperature	≥120	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.04	%	-
Melt Temperature Optimum	250	°C	-
Min. melt temperature	240	°C	-

Revised: 2017-08-14

Page: 2 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Crastin® FG6129 NC010

## THERMOPLASTIC POLYESTER RESIN

Max. melt temperature	260	°C	-
Mold Temperature Optimum	80	°C	-
Min. mould temperature	30	°C	-
Max. mould temperature	130	°C	-
Hold pressure range	≥60	MPa	-
Hold pressure time	4	s/mm	-
Back pressure	As low as possible		-
Ejection temperature	170	°C	-

Extrusion	Value	Unit	Test Standard
Drying Temperature	110 - 130	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.04	%	-
Melt Temperature Optimum	250	°C	-
Melt Temperature Range	240 - 260	°C	-

Characteristics			
Processing	<ul style="list-style-type: none"><li>• Injection Moulding</li><li>• Profile Extrusion</li></ul>	<ul style="list-style-type: none"><li>• Sheet Extrusion</li><li>• Other Extrusion</li></ul>	<ul style="list-style-type: none"><li>• Coatable</li></ul>
Delivery form	<ul style="list-style-type: none"><li>• Pellets</li></ul>		
Regional Availability	<ul style="list-style-type: none"><li>• North America</li><li>• Europe</li></ul>	<ul style="list-style-type: none"><li>• Asia Pacific</li><li>• South and Central America</li></ul>	<ul style="list-style-type: none"><li>• Near East/Africa</li><li>• Global</li></ul>

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

### Asia Pacific

Tel: +81 3 5521 8600

### Europe/Middle East/Africa

Tel: +41 22 717 51 11



# DuPont™ Crastin® FG6129 NC010

## THERMOPLASTIC POLYESTER RESIN

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✗ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

#### Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

#### Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✓ Ethanol (23 °C)

#### Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

#### Ketones

- ✓ Acetone (23 °C)

#### Ethers

- ✓ Diethyl ether (23 °C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)

#### Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5 (60 °C)
- ✗ ISO 1817 Liquid 2 - M15E4 (60 °C)
- ✗ ISO 1817 Liquid 3 - M3E7 (60 °C)
- ✗ ISO 1817 Liquid 4 - M15 (60 °C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)

Revised: 2017-08-14

Page: 4 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Crastin® FG6129 NC010

## THERMOPLASTIC POLYESTER RESIN

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

### Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✗ DOT No. 4 Brake fluid (130°C)
- ✗ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✗ Water (90°C)
- ✓ Phenol solution (5% by mass) (23°C)

### Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

- ✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 4mm (Hytrel® measured at 2 mm), IEC Electrical properties measured at 2mm, all ASTM properties measured at 3.2mm, and test temperatures are 23°C unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

Revised: 2017-08-14

Page: 5 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

#### Asia Pacific

Tel: +81 3 5521 8600

#### Europe/Middle East/Africa

Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.