

CYCOLAC™ RESIN DL200H

REGION AMERICAS

DESCRIPTION

CYCOLAC DL200H is a hydrostable high heat ABS/PC blend

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	47	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	70	%	ASTM D 638
Tensile Modulus, 5 mm/min	2330	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	77	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2200	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	49	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.9	%	ISO 527
Tensile Strain, break, 50 mm/min	75	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	2100	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	620	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	500	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -40°C	21	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	65	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	30	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	118	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	96	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	101	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	112	°C	ISO 306
Vicat Softening Temp, Rate B/120	114	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	96	°C	ISO 75/Af
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 260°C/5.0 kgf	25	g/10 min	ASTM D 1238
Density	1.11	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	9	g/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	100 – 105	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	260 – 290	°C	
Nozzle Temperature	260 – 290	°C	
Front - Zone 3 Temperature	255 – 290	°C	
Middle - Zone 2 Temperature	255 – 290	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	75 – 100	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.