

# CYCOLAC™ RESIN EX75

REGION ASIA

## DESCRIPTION

Multi-purpose, extrusion ABS providing a favorable balance of engineering properties.

## TYPICAL PROPERTY VALUES

Revision 20171006

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	39	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	33	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	42.9	%	ASTM D 638
Tensile Modulus, 5 mm/min	2130	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	73	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	421	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	35	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	106	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	94	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	82	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E 831
<b>PHYSICAL</b>			
Specific Gravity	1.04	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.5 – 0.7	%	SABIC method
Melt Viscosity, 240°C, 100 sec-1	11600	Poise	ASTM D 3825
Melt Volume Rate, MVR at 220°C/10.0 kg	9	cm <sup>3</sup> /10 min	ISO 1133
<b>SHEET EXTRUSION</b>			
Drying Temperature	90 – 95	°C	
Drying Time (Cumulative)	4	hrs	
Maximum Moisture Content	0	%	
Melt Temperature	200 – 220	°C	
Barrel - Zone 1 Temperature	170 – 190	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Barrel - Zone 2 Temperature	180 – 200	°C	
Barrel - Zone 3 Temperature	175 – 205	°C	
Barrel - Zone 4 Temperature	180 – 210	°C	
Adapter Temperature	180 – 205	°C	
Die Temperature	180 – 215	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.