

## WONDERLOY<sup>®</sup>

PC alloy, general purpose injection molding application

PROPERTIES	CONDITION	PC-330	PC-345	PC-365	PC-385	UNIT	METHOD
<b><u>PHYSICAL</u></b>							
Melt Flow Index	260°C/5kg	13	17	20	20	g/10min	ASTM D-1238
Spiral Flow Length	260°C, 2mm V:50%,	35	33	30	28	cm	Chimei method
Specific Gravity	P:50% 23°C	1.08	1.10	1.13	1.15	-	ASTM D-792
Mold Shrinkage	-	0.4~0.6	0.4~0.6	0.4~0.6	0.4~0.6	%	ASTM D-955
Rockwell Hardness	23°C	R-108	R-108	R-115	R-114	-	ASTM D-785
CLTE	Flow:-40°C-40°C	9.0E-06	8.5E-06	8.0E-05	7.5E-05	cm/cm/°C	ASTM E-831
<b><u>MECHANICAL</u></b>							
Tensile Strength @ Yield	50mm/min	500	500	540	540	kg/cm <sup>2</sup>	ASTM D-638
Tensile Elongation @ Break	50mm/min	85	85	85	90	%	ASTM D-638
Flexural Strength	1.3mm/min	750	750	800	800	kg/cm <sup>2</sup>	ASTM D-790
Flexural Modulus	1.3mm/min	23,000	23,000	23,000	23,500	kg/cm <sup>2</sup>	ASTM D-790
Izod Impact (1/8")	Notched, 23°C	45	50	55	60	kg-cm/cm	ASTM D-256
Izod Impact (1/8")	Notched, -30°C	40	45	50	50	kg-cm/cm	ASTM D-256
<b><u>THERMAL</u></b>							
Heat Distortion Temp. (unannealed)	3.2mm, 1.82Mpa 120°C/hr	88	95	106	110	°C	ASTM D-648
	6.4mm, 1.82Mpa 120°C/hr	98	105	115	118		
Vicat Softening Temp. (unannealed)	1kg, 50°C/hr	118	125	136	140	°C	ASTM D-1525
	5kg, 50°C/hr	108	110	125	133		
<b><u>ELECTRICAL</u></b>							
Dielectric Constant	1 MHz	3.1	3.1	3.1	3.0	-	IEC 60250
Volume Resistivity	-	1E+16	1E+16	1E+16	1E+16	Ohm*m	IEC 60093
Surface Resistivity	-	1E+16	1E+16	1E+16	1E+16	Ohm	IEC 60093
<b><u>FLAMMABILITY</u></b>							
Flame Rating_HB		1.5	1.5	1.5	1.5	mm	UL-94
<b><u>PROCESSING PARAMETERS</u></b>							
Drying Temperature		80~100	80~100	80~100	80~100	°C	
Drying Time		4	4	4	4	Hrs	
Barrel Temperature		230~270	230~270	230~270	240~280	°C	
Mold Temperature		50~100	50~100	50~100	50~100	°C	

All figures listed here is for reference, not guaranteed.

Final revised date: 2014/6

# CHIMEI

奇美實業股份有限公司

CHIMEI CORPORATION

網址: [www.cn-plas.com](http://www.cn-plas.com)

---

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its

Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.