

CHIMEI

奇美實業股份有限公司
CHI MEI CORPORATION

台南市仁德區三甲里59-1號
59-1, San Chia, Jen Te, Tainan City 71702, Taiwan
TEL: 886-6-266-5000 FAX: 886-6-266-5555~7

WONDERLITE® PC-6600

無鹵阻燃 PC · 高耐熱、高耐衝的特性可使用於電源供應產業

物性項目	條件	數值	單位	測試方法
物理特性				
熔融指數	300°C/1.2kg	10	g/10min	ASTM D-1238
比重	23°C	1.2	---	ASTM D-792
收縮率		0.5~0.7	%	ASTM D-955
洛式硬度	23°C	R-122	---	ASTM D-785
線膨脹係數	Flow:23-55°C	6.70E-05	cm/cm/°C	ISO11359-2
機械特性				
拉伸強度 @ Yield	50mm/min	630	kg/cm ²	ASTM D-638
延伸率 @ Break	50mm/min	100	%	ASTM D-638
彎曲強度	1.3mm/min	920	kg/cm ²	ASTM D-790
彎曲模量	1.3mm/min	24000	kg/cm ²	ASTM D-790
Izod 衝擊強度 (1/8")	Notched, 23°C	70	kg-cm/cm	ASTM D-256
Izod 衝擊強度 (1/8")	Notched, -30°C	15	kg-cm/cm	ASTM D-256
耐熱性質				
熱變形溫度 (未退火)	3.2mm,1.82Mpa 120°C/hr	125	°C	ASTM D-648
	6.4mm,1.82Mpa 120°C/hr	135		
維卡軟化點 (未退火)	1kg, 50°C/hr	150	°C	ASTM D-1525
	5kg, 50°C/hr	145		

CHIMEI

奇美實業股份有限公司
CHI MEI CORPORATION

台南市仁德區三甲里59-1號
59-1, San Chia, Jen Te, Tainan City 71702, Taiwan
TEL: 886-6-266-5000 FAX: 886-6-266-5555~7

電器性質

介電常數	1MHz	3	--	IEC 60250
體積阻抗	--	1E+16	Ohm*m	IEC 60093
表面阻抗	--	1E+16	Ohm	IEC 60093

阻燃性

防火等級_V0		1.1	mm	UL-94
---------	--	-----	----	-------

建議加工條件

烘料溫度		120	°C
烘料時間		4	Hrs
料管溫度		270~300	°C
模具溫度		70~100	°C

All figures listed here is for reference, not guaranteed.

Final revised date : 2014/6

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.