

# PP

High Heat Resistance Resin for Retort Pouch

## ▶ BI300

### ● Description

**BI300** is a high isotactic Block Copolymer which has higher crystallinity, compared to general PP. Due to high crystalline nature & optimum rubber design, BI300 has an excellent property balance between high stiffness and impact strength. Films made from this grade provide high heat resistance and superior mechanical strength, thus this grade is highly suited to retort pouch film application.

### ● Characteristics

- ▶ Good balance physical property between stiffness & impact strength
- ▶ Punch resistance
- ▶ Heat resistance
- ▶ High transparency

### ● Applications

- ▶ Retort pouch, Cast film

### ● Physical Properties

Typical Properties	Method (ASTM)	Unit	BI300
Melt flow index	D1238	g/10min	5
Density	D1505	g/cm <sup>3</sup>	0.91
Tensile strength at yield	D638	kg/cm <sup>2</sup>	310
Elongation at break	D638	%	>500
Flexural modulus	D790	kg/cm <sup>2</sup>	14,500
Izod impact strength at 23°C	D256	kgcm/cm	9
Rockwell hardness	D785	R-scale	80
Heat distortion temp.	D648	°C	109

\* Data shown above are representative values for reference purposes only, and not to be construed as specifications.

## ● **Food Contact Application**

- ▶ Hanwha Total BI300 meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

## ● **Contacts**

---

- ▶ **Product Information & Technical Services** [www.cn-plas.com](http://www.cn-plas.com)

### Disclaimer

*This [www.cn-plas.com](http://www.cn-plas.com) document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE*

*GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.*