

VALOXTM RESIN 4012G

REGION EUROPE

DESCRIPTION

VALOX 4012G is a 10% glass fiber reinforced PBT injection molding resin with excellent mechanical properties. Applications: connectors. This grade is a 4012 with improved cycle time and ductility.

TYPICAL PROPERTY VALUES

Revision 20190204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	80	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	80	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	4400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3800	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	4500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	125	MPa	ISO 178
Flexural Stress, break, 2 mm/min	120	MPa	ISO 178
Flexural Strain, break, 2 mm/min	5	%	ISO 178
Flexural Modulus, 2 mm/min	3800	MPa	ISO 178
Hardness, H358/30	110	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT			
Charpy Impact, unnotched, 23°C	33	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	33	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	380	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	380	J/m	ASTM D 4812
Izod Impact, notched, 23°C	50	J/m	ASTM D 256
Izod Impact, notched, 0°C	50	J/m	ASTM D 256
Izod Impact, notched, -30°C	50	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	4	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy Impact, notched, 23°C	6	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -30°C	6	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	205	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.63E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	4.79E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	2.11E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	205	°C	ISO 306
Vicat Softening Temp, Rate B/120	200	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	215	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	170	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	185	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.35	-	ASTM D 792
Filler Content	10	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow	0.6 – 0.9	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.6 – 1.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.7 – 1	%	SABIC method
Melt Flow Rate, 250°C/1.2 kgf	10	g/10 min	ASTM D 1238
Melt Flow Rate, 266°C/5.0 kgf	90	g/10 min	ASTM D 1238
Density	1.35	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/1.2 kg	9	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	50	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	80	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	110	Pa-s	ISO 11443
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	ASTM D 149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.4	-	ASTM D 150
Dissipation Factor, 1 MHz	0.015	-	ASTM D 150
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.015	-	IEC 60250
Comparative Tracking Index	325	V	IEC 60112
Comparative Tracking Index, M	150	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.1	-	IEC 60250
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.