

VALOXTM RESIN 8032U

REGION EUROPE

DESCRIPTION

VALOX 8032U is a 30% glass fibre reinforced, UV stabilized PBT+PET blend with excellent surface finish. Applications: appliance housings, door handles, mirror brackets.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	9950	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	165	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8450	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	145	MPa	ISO 527
Tensile Stress, break, 5 mm/min	145	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.4	%	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	9500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	210	MPa	ISO 178
Flexural Modulus, 2 mm/min	8500	MPa	ISO 178
Hardness, H358/30	110	MPa	ISO 2039-1
Hardness, Rockwell R	119	-	ISO 2039-2
IMPACT			
Izod Impact, unnotched, 23°C	480	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	470	J/m	ASTM D 4812
Izod Impact, notched, 23°C	57	J/m	ASTM D 256
Izod Impact, notched, -30°C	48	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	8	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	40	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	40	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D 1525

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	202	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	208	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	190	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E 831
CTE, 23°C to 60°C, flow	2.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.1E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	202	°C	ISO 306
Vicat Softening Temp, Rate B/120	204	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	217	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	195	°C	ISO 75/Ae
PHYSICAL			
Specific Gravity	1.58	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.8	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.6 – 1	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 1	%	SABIC method
Melt Flow Rate, 265°C/2.16kgf	15	g/10 min	ASTM D 1238
Density	1.53	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.16	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.05	%	ISO 62
Melt Volume Rate, MVR at 265°C/2.16 kg	15	cm ³ /10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	27	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Relative Permittivity, 100 Hz	3.6	-	IEC 60250
Relative Permittivity, 1 MHz	3.2	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0008	-	IEC 60250
Dissipation Factor, 1 MHz	0.013	-	IEC 60250
Comparative Tracking Index	300	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 285	°C	
Nozzle Temperature	265 – 275	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 110	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.