

VALOXTM RESIN K4530

REGION ASIA

DESCRIPTION

15% glass reinforced PBT, Hydrolytically stable, High flow, Automotive connectors.

TYPICAL PROPERTY VALUES

Revision 20181115

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	103	MPa	SABIC - Japan Method
Tensile Strain, break	4 – 4	%	SABIC - Japan Method
Flexural Stress	151	MPa	ASTM D 790
Flexural Modulus	4630	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	194	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	218	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.41	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.9	%	SABIC method
Mold Shrinkage, flow, 6.4 mm	1 – 1.2	%	SABIC method

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.