

VALOXTM RESIN V8280

REGION EUROPE

DESCRIPTION

40% GR PBT+PET. High stiffness. Excellent surface aesthetics. Applications include office furniture.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	145	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	145	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.2	%	ASTM D 638
Tensile Modulus, 5 mm/min	12750	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	220	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	10680	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	827	J/m	ASTM D 4812
Izod Impact, notched, 23°C	106	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	7	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	221	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	193	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.44E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.38E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.64	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.5	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.8	%	SABIC method
Melt Flow Rate, 266°C/5.0 kgf	33	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 265°C/5.0 kg	22	cm ³ /10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	135	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 280	°C	
Nozzle Temperature	270 – 280	°C	
Front - Zone 3 Temperature	270 – 280	°C	
Middle - Zone 2 Temperature	270 – 280	°C	
Rear - Zone 1 Temperature	260 – 275	°C	
Mold Temperature	40 – 65	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.025 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.