

LEXANTM RESIN 244R

REGION ASIA

DESCRIPTION

10.5 MFR. Improved flame retardance. USA FDA compliant (limited colors). Internal mold release.

TYPICAL PROPERTY VALUES

Revision 20190527

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|--------------------|--------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 62 | MPa | ASTM D 638 |
| Tensile Stress, brk, Type I, 50 mm/min | 68 | MPa | ASTM D 638 |
| Tensile Strain, yld, Type I, 50 mm/min | 7 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 50 mm/min | 130 | % | ASTM D 638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 96 | MPa | ASTM D 790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2340 | MPa | ASTM D 790 |
| Hardness, Rockwell M | 70 | - | ASTM D 785 |
| Hardness, Rockwell R | 118 | - | ASTM D 785 |
| Taber Abrasion, CS-17, 1 kg | 10 | mg/1000cy | ASTM D 1044 |
| IMPACT | | | |
| Izod Impact, unnotched, 23°C | 3204 | J/m | ASTM D 4812 |
| Izod Impact, notched, 23°C | 801 | J/m | ASTM D 256 |
| Tensile Impact, Type S | 577 | kJ/m ² | ASTM D 1822 |
| Falling Dart Impact (D 3029), 23°C | 169 | J | ASTM D 3029 |
| THERMAL | | | |
| Vicat Softening Temp, Rate B/50 | 154 | °C | ASTM D 1525 |
| HDT, 0.45 MPa, 6.4 mm, unannealed | 137 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 6.4 mm, unannealed | 132 | °C | ASTM D 648 |
| CTE, -40°C to 95°C, flow | 6.84E-05 | 1/°C | ASTM E 831 |
| Specific Heat | 1.25 | J/g·°C | ASTM C 351 |
| Thermal Conductivity | 0.27 | W/m·°C | ASTM C 177 |
| Relative Temp Index, Elec | 130 | °C | UL 746B |
| Relative Temp Index, Mech w/impact | 130 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact | 130 | °C | UL 746B |
| PHYSICAL | | | |
| Specific Gravity | 1.2 | - | ASTM D 792 |
| Specific Volume | 0.83 | cm ³ /g | ASTM D 792 |
| Density | 1.19 | g/cm ³ | ASTM D 792 |
| Water Absorption, 24 hours | 0.15 | % | ASTM D 570 |
| Water Absorption, equilibrium, 23°C | 0.35 | % | ASTM D 570 |
| Water Absorption, equilibrium, 100°C | 0.58 | % | ASTM D 570 |
| Mold Shrinkage, flow, 3.2 mm | 0.5 – 0.7 | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 10.5 | g/10 min | ASTM D 1238 |
| OPTICAL | | | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|----------|--------------|
| Light Transmission, 2.54 mm | 88 | % | ASTM D 1003 |
| Haze, 2.54 mm | 1 | % | ASTM D 1003 |
| Refractive Index | 1.586 | - | ASTM D542 |
| ELECTRICAL | | | |
| Volume Resistivity | >1.E+17 | Ohm-cm | ASTM D 257 |
| Dielectric Strength, in air, 3.2 mm | 14.9 | kV/mm | ASTM D 149 |
| Relative Permittivity, 50/60 Hz | 3.17 | - | ASTM D 150 |
| Relative Permittivity, 1 MHz | 2.96 | - | ASTM D 150 |
| Dissipation Factor, 50/60 Hz | 0.0009 | - | ASTM D 150 |
| Dissipation Factor, 1 MHz | 0.01 | - | ASTM D 150 |
| Hot Wire Ignition {PLC} | 2 | PLC Code | UL 746A |
| High Voltage Arc Track Rate {PLC} | 2 | PLC Code | UL 746A |
| High Ampere Arc Ign, surface {PLC} | 1 | PLC Code | UL 746A |
| Comparative Tracking Index (UL) {PLC} | 2 | PLC Code | UL 746A |
| FLAME CHARACTERISTICS | | | |
| UL Recognized, 94V-2 Flame Class Rating | 1.47 | mm | UL 94 |
| UL Recognized, 94V-0 Flame Class Rating | 5.99 | mm | UL 94 |
| Oxygen Index (LOI) | 25 | % | ASTM D 2863 |
| INJECTION MOLDING | | | |
| Drying Temperature | 120 | °C | |
| Drying Time | 3 – 4 | hrs | |
| Drying Time (Cumulative) | 48 | hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 295 – 315 | °C | |
| Nozzle Temperature | 290 – 310 | °C | |
| Front - Zone 3 Temperature | 295 – 315 | °C | |
| Middle - Zone 2 Temperature | 280 – 305 | °C | |
| Rear - Zone 1 Temperature | 270 – 295 | °C | |
| Mold Temperature | 70 – 95 | °C | |
| Back Pressure | 0.3 – 0.7 | MPa | |
| Screw Speed | 40 – 70 | rpm | |
| Shot to Cylinder Size | 40 – 60 | % | |
| Vent Depth | 0.025 – 0.076 | mm | |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.