

LEXANTM FR RESINS LUX7189

REGION AMERICAS

DESCRIPTION

LEXAN LUX7189 is an injection moldable polycarbonate (PC) with an MVR (300°C/1.2kg) 23. It contains non-brominated, non-chlorinated flame retardant systems with UL-94 V0@1.5mm rating. It is designed for high light reflectance and shielding applications with good UV weathering capability.

TYPICAL PROPERTY VALUES

Revision 20190613

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Tensile Modulus, 50 mm/min	2700	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	98	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2700	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	2140	J/m	ASTM D 4812
Izod Impact, notched, 23°C	150	J/m	ASTM D 256
Izod Impact, notched, -30°C	100	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	59	J	ASTM D 3763
THERMAL			
Vicat Softening Temp, Rate B/50	140	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	125	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.5E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.3	-	ASTM D 792
Density	1.3	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	22	g/10 min	ASTM D 1238
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	3	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	2.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	265 – 290	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.