

# LEXAN<sup>TM</sup> RESIN EX1632T

REGION AMERICAS

## DESCRIPTION

LEXAN EX1632T polycarbonate resin is designed for use in multi-wall sheet or profile extrusion applications. It contains branched polycarbonate resin, release, and UV stabilizer. It is available in a limited number of colors.

## TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	61	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6.3	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	98.8	%	ASTM D 638
Tensile Modulus, 5 mm/min	2210	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	99	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2370	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	800	J/m	ASTM D 256
Izod Impact, notched, -30°C	152	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	74	J	ASTM D 3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	145	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	140	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.6E-05	1/°C	ASTM E 831
Vicat Softening Temp, Rate B/120	147	°C	ISO 306
<b>PHYSICAL</b>			
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	6	g/10 min	ASTM D 1238
Density	1.19	g/cm <sup>3</sup>	ISO 1183
<b>FLAME CHARACTERISTICS</b>			
UL Yellow Card Link	<a href="#">E121562-100989271</a>	-	-
UL Compliant, 94HB Flame Class Rating	0.8	mm	UL 94 by SABIC-IP
<b>MULTIWALL SHEET EXTRUSION</b>			
Drying Temperature	120	°C	
Drying Time	2 – 4	hrs	
Barrel - Zone 1 Temperature	240 – 270	°C	
Barrel - Zone 2 Temperature	240 – 270	°C	
Barrel - Zone 3 Temperature	240 – 270	°C	
Hopper Temperature	100 – 120	°C	
Adapter Temperature	220 – 260	°C	
Die Temperature	220 – 280	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	220 – 280	°C	
Calibrator Temperature	50 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.