

Vydyne® 909

polyamide 66/6 copolymer



Vydyne 909 is an halogenated, 25% glass-filled, flame-retardant PA66/6 copolymer with excellent strength and toughness. It is lubricated for machine feed and easy mold release and has an

Underwriters Laboratories UL 94 flammability classification of V-0 at 0.4 mm (0.016") thick.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight			
Additive	• Flame Retardant	• Halogen	• Lubricant	
Features	• Crack Resistant	• Good Toughness	• High Strength	
	• Flame Retardant	• Halogenated	• Ignition Resistant	
	• Good Mold Release	• High Rigidity	• Lubricated	
Uses	• Appliances	• Electrical Parts		
	• Automotive Electronics	• Electrical/Electronic Applications	• Living Hinges	
	• Bobbins	• Housings	• Printed Circuit Boards	
	• Connectors	• Industrial Applications	• Switches	
	• Electrical Housing	• Lighting Applications		
RoHS Compliance	• RoHS Compliant			
Automotive Specifications	• DELPHI M-6538V	• GM GMP.PA66.058		
UL File Number	• E70062			
Appearance	• Natural Color			
Forms	• Pellets			
Processing Method	• Injection Molding			

Physical	Dry	Conditioned	Unit	Test Method
Density	1.47	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.0	--	%	
Flow : 23°C, 2.00 mm	0.40	--	%	
Water Absorption				ISO 62
24 hr, 23°C	0.70	--	%	
Equilibrium, 23°C, 50% RH	1.3	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9100	7100	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	132	90.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.2	3.0	%	ISO 527-2
Flexural Modulus (23°C)	8300	5000	MPa	ISO 178
Flexural Strength (23°C)	193	140	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	9.5	--	kJ/m ²	
23°C	9.4	--	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	35	--	kJ/m ²	
23°C	40	--	kJ/m ²	
Notched Izod Impact Strength (23°C)	9.0	--	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	--	°C	ISO 75-2/A
Melting Temperature	250	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	1.0E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.40 mm	65.0	--	°C	
0.75 mm	130	--	°C	
1.5 mm	130	--	°C	
3.0 mm	130	--	°C	
RTI Imp				UL 746
0.40 mm	65.0	--	°C	
0.75 mm	65.0	--	°C	
1.5 mm	95.0	--	°C	
3.0 mm	95.0	--	°C	
RTI Str				UL 746
0.40 mm	65.0	--	°C	
0.75 mm	110	--	°C	
1.5 mm	110	--	°C	
3.0 mm	110	--	°C	

Electrical	Dry	Conditioned	Unit	Test Method
Arc Resistance (3.00 mm)	PLC 6	--		ASTM D495
Comparative Tracking Index (3.00 mm)	250 to 399	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.75 mm	PLC 0	--		
1.5 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)				UL 746
3.00 mm	PLC 3	--		
Hot-wire Ignition (HWI)				UL 746
0.75 mm	PLC 0	--		
1.5 mm	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.40 mm	V-0	--		
0.75 mm	V-0	--		
1.5 mm	• V-0 • 5VA	--		
3.0 mm	• V-0 • 5VA	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.40 mm	960	--	°C	
0.75 mm	960	--	°C	
1.5 mm	960	--	°C	
3.0 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.40 mm	930	--	°C	
0.75 mm	750	--	°C	
1.5 mm	750	--	°C	
3.0 mm	800	--	°C	
Oxygen Index	32	--	%	ISO 4589-2

Injection	Dry Unit
Drying Temperature	80 °C
Drying Time	4.0 hr
Suggested Max Regrind	25 %
Rear Temperature	240 to 270 °C
Middle Temperature	240 to 270 °C
Front Temperature	240 to 270 °C
Nozzle Temperature	240 to 270 °C
Processing (Melt) Temp	250 to 270 °C
Mold Temperature	65 to 95 °C

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.