

Amodel® ET-1000 HS

polyphthalamide

Amodel® ET-1000 HS is an impact modified, heat stabilized polyphthalamide (PPA) that exhibits exceptional impact strength and toughness. Like all Amodel® PPA resins, ET-1000 HS offers high fatigue strength, good chemical

resistance and high mechanical property retention over a broad temperature and humidity range.

- Natural: ET-1000 HS NT

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Additive	• Heat Stabilizer	• Impact Modifier
Features	• Chemical Resistant • Ductile • Heat Stabilized	• Hot Water Moldability • Impact Modified • Low Warp
Uses	• Automotive Applications • Automotive Electronics • Automotive Under the Hood • Connectors • General Purpose • Housings	• Industrial Applications • Industrial Parts • Lawn and Garden Equipment • Machine/Mechanical Parts • Metal Replacement
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• ASTM D4000 PA1234 Color: BK684 Black • ASTM D4000 PA1234 Color: NT Natural • ASTM D6779 PA1234 • DELPHI 23295267 Color: BK-684 Black • DELPHI 23295267 Color: NT Natural	• DELPHI 28213409 Color: BK-684 Black • DELPHI 28213409 Color: NT Natural • DELPHI M-2965 Color: BK684 Black • DELPHI M-2965 Color: NT Natural • DELPHI MSP24103175 Color: NT Natural
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Water-Heated Mold Injection Molding	

Physical	Dry	Conditioned	Unit	Test method
Density	1.13	--	g/cm ³	ISO 1183/A
Molding Shrinkage				ASTM D955
Flow	1.5	--	%	
Across Flow	1.5	--	%	
Water Absorption (24 hr)	0.70	--	%	ASTM D570

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				
--	2410	2410	MPa	ASTM D638
23°C	2410	--	MPa	ISO 527-2
100°C	2000	--	MPa	ISO 527-2

Amodel® ET-1000 HS

polyphthalamide

Mechanical	Dry	Conditioned	Unit	Test method
Tensile Stress				
Yield, 23°C	70.3	--	MPa	ISO 527-2
Yield, 100°C	33.8	--	MPa	ISO 527-2
Break, 23°C	60.0	--	MPa	ISO 527-2
-40°C	110	96.5	MPa	ASTM D638
23°C	68.9	62.7	MPa	ASTM D638
Tensile Elongation				
Yield, -40°C	9.0	9.0	%	ASTM D638
Yield, 23°C	6.0	6.0	%	ASTM D638
Yield, 23°C	5.0	--	%	ISO 527-2
Yield, 100°C	4.3	--	%	ISO 527-2
Break, -40°C	12	11	%	ASTM D638
Break, 23°C	20	18	%	ASTM D638
Break, 23°C	7.0	--	%	ISO 527-2
Break, 100°C	95	--	%	ISO 527-2
Flexural Modulus				
--	2280	2140	MPa	ASTM D790
23°C	1790	--	MPa	ISO 178
100°C	1310	--	MPa	ISO 178
Flexural Strength				
--	109	85.5	MPa	ASTM D790
23°C	70.3	--	MPa	ISO 178
100°C	44.1	--	MPa	ISO 178
Shear Strength				
	58.6	--	MPa	ASTM D732
Taber Abrasion Resistance				
1000 Cycles, 1000 g, CS-17 Wheel	6.00	--	mg	ASTM D1044
Impact				
Charpy Notched Impact Strength (23°C)				
	78	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)				
	No Break	--		ISO 179/1eU
Notched Izod Impact				
-40°C	110	--	J/m	ASTM D256
23°C	910	1100	J/m	ASTM D256
23°C	73	--	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)				
	No Break	--		ISO 180/1U
Instrumented Dart Impact				
				ASTM D3763
Energy to Maximum Load ¹	38.0	--	J	
Total Energy	54.2	--	J	
Hardness				
Rockwell Hardness (R-Scale)				
	120	--		ASTM D785
Thermal				
Heat Deflection Temperature				
1.8 MPa, Unannealed	109	--	°C	ISO 75-2/A
1.8 MPa, Annealed	120	--	°C	ASTM D648
Melting Temperature				
	310	--	°C	ISO 11357-3 ASTM D3418

Amodel® ET-1000 HS

polyphthalamide

Thermal	Dry	Conditioned Unit	Test method
CLTE			ASTM E831
Flow : 0 to 100°C	7.7E-5	-- cm/cm/°C	
Flow : 100 to 200°C	1.4E-4	-- cm/cm/°C	
Transverse : 0 to 100°C	8.1E-5	-- cm/cm/°C	
Transverse : 100 to 200°C	1.1E-4	-- cm/cm/°C	

Injection	Dry Unit
Drying Temperature	110 °C
Drying Time	4.0 hr
Suggested Max Moisture	0.030 to 0.060 %
Rear Temperature	304 to 318 °C
Front Temperature	316 to 329 °C
Processing (Melt) Temp	321 to 343 °C
Mold Temperature	> 135 °C

Injection Notes

MOLD TEMPERATURE

- If the wall is thick, lower temperatures may be used to prevent ejector pin problems.

STORAGE:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Notes

Typical properties: these are not to be construed as specifications.

¹ Maximum Load: 1050 lb (4670 N)

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.

