

LEXANTM COPOLYMER EXL6414

REGION ASIA

DESCRIPTION

PC-Siloxane copolymer with excellent processability. Impact modified, medium flow, extreme low temp. ductility.

TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	55	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	59	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 50 mm/min	1720	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	79	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1990	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	54	MPa	ISO 527
Tensile Stress, break, 50 mm/min	58	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	88	%	ISO 527
Tensile Modulus, 1 mm/min	2270	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2090	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	801	J/m	ASTM D 256
Izod Impact, notched, -30°C	694	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	62	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	61	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	70	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	60	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	70	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	141	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	136	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	122	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.02E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	6.9E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 80°C, xflow	7.3E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	136	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	8	g/10 min	ASTM D 1238
Density	1.18	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	7	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.7E+17	Ohm-cm	IEC 60093
Surface Resistivity, ROA	4.1E+17	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.6	-	IEC 60250
Dissipation Factor, 1 MHz	0.0094	-	IEC 60250
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥3	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-228451	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.