

# LEXAN<sup>TM</sup> COPOLYMER FXD9810

REGION AMERICAS

## DESCRIPTION

Non-chlorinated, non-brominated Flame retardant PC-siloxane copolymer blend. Excellent processability, super high flow, good impact, UL rated V-0. Limited translucent colors.

## TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	55	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	50	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 50 mm/min	2200	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	94	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	49	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.6	%	ISO 527
Tensile Strain, break, 50 mm/min	95	%	ISO 527
Tensile Modulus, 1 mm/min	2150	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	91	MPa	ISO 178
Flexural Modulus, 2 mm/min	2250	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	690	J/m	ASTM D 256
Izod Impact, notched, -30°C	220	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	63	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	40	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	19	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	49	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	136	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.05E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.03E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	6.9E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	6.8E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	137	°C	ISO 306
Vicat Softening Temp, Rate B/120	138	°C	ISO 306
Relative Temp Index, Elec <sup>(1)</sup>	120	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	110	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	120	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>PHYSICAL</b>			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	30	g/10 min	ASTM D 1238
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.26	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	29	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 2	≥1	mm	UL 746A
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-592770</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.2	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1	mm	UL 94
Glow Wire Ignitability Temperature, 1.2 mm	875	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 1.2 mm	930	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	875	°C	IEC 60695-2-12
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	265 – 290	°C	
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.