

LEXANTM FR RESINS 3413HF

REGION AMERICAS

DESCRIPTION

30% glass reinforced, high flow PC.

TYPICAL PROPERTY VALUES

Revision 20200326

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	99	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	153	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6610	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	69	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	137	°C	ASTM D 648
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.44	-	ASTM D 792
Melt Flow Rate, 300°C/5.0 kgf	40	g/10 min	ASTM D 1238
ELECTRICAL			
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220882	-	-
UL Recognized, 94V-1 Flame Class Rating	1.47	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	2.99	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.