

# Makrolon® LED5101

/ MVR (300 °C/1.2 kg) 34 cm<sup>3</sup>/10 min; light guides; PC with highest transmission; low viscosity; easy release; injection molding - melt temperature 280 - 320 °C

## ISO Shortname

| Property  | Test Condition      | Unit                    | Standard                  | typical Value |
|---|---------------------|-------------------------|---------------------------|---------------|
| <b>Rheological properties</b>                   |                     |                         |                           |               |
| C Melt volume-flow rate                         | 300 °C/ 1.2 kg      | cm <sup>3</sup> /10 min | ISO 1133                  | 34            |
| C Molding shrinkage, parallel                   | 60x60x2 mm/ 500 bar | %                       | ISO 294-4                 | 0.65          |
| C Molding shrinkage, normal                     | 60x60x2 mm/ 500 bar | %                       | ISO 294-4                 | 0.7           |
| <b>Mechanical properties (23 °C/50 % r. h.)</b> |                     |                         |                           |               |
| C Tensile modulus                               | 1 mm/min            | MPa                     | ISO 527-1,-2              | 2350          |
| C Yield stress                                  | 50 mm/min           | MPa                     | ISO 527-1,-2              | 63            |
| C Yield strain                                  | 50 mm/min           | %                       | ISO 527-1,-2              | 6.0           |
| C Nominal strain at break                       | 50 mm/min           | %                       | ISO 527-1,-2              | > 50          |
| Stress at break                                 | 50 mm/min           | MPa                     | ISO 527-1,-2              | 60            |
| Strain at break                                 | 50 mm/min           | %                       | b.o. ISO 527-1,-2         | 125           |
| Flexural modulus                                | 2 mm/min            | MPa                     | ISO 178                   | 2350          |
| Flexural strength                               | 2 mm/min            | MPa                     | ISO 178                   | 97            |
| Flexural strain at flexural strength            | 2 mm/min            | %                       | ISO 178                   | 7.1           |
| Flexural stress at 3.5 % strain                 | 2 mm/min            | MPa                     | ISO 178                   | 73            |
| C Charpy impact strength                        | 23 °C               | kJ/m <sup>2</sup>       | ISO 179/1eU               | N             |
| C Charpy impact strength                        | -30 °C              | kJ/m <sup>2</sup>       | ISO 179/1eU               | N             |
| Charpy impact strength                          | -60 °C              | kJ/m <sup>2</sup>       | ISO 179/1eU               | N             |
| Charpy notched impact strength                  | 23 °C/ 3 mm         | kJ/m <sup>2</sup>       | ISO 7391/b.o. ISO 179/1eA | 60P(C)        |
| Charpy notched impact strength                  | -30 °C/ 3 mm        | kJ/m <sup>2</sup>       | ISO 7391/b.o. ISO 179/1eA | 12C           |
| Izod notched impact strength                    | 23 °C/ 3 mm         | kJ/m <sup>2</sup>       | ISO 7391/b.o. ISO 180/A   | 55P           |
| Izod notched impact strength                    | -30 °C/ 3 mm        | kJ/m <sup>2</sup>       | ISO 7391/b.o. ISO 180/A   | 12C           |
| C Puncture impact properties - maximum force    | 23 °C               | N                       | ISO 6603-2                | 4900          |
| C Puncture impact properties - maximum force    | -30 °C              | N                       | ISO 6603-2                | 5900          |
| C Puncture energy                               | 23 °C               | J                       | ISO 6603-2                | 55            |
| C Puncture energy                               | -30 °C              | J                       | ISO 6603-2                | 60            |
| Ball indentation hardness                       |                     | N/mm <sup>2</sup>       | ISO 2039-1                | 115           |

# Makrolon® LED5101

| Property  | Test Condition    | Unit                | Standard       | typical Value |
|---|-------------------|---------------------|----------------|---------------|
| <b>Thermal properties</b>   |                   |                     |                |               |
| C Glass transition temperature  | 10 °C/min         | °C                  | ISO 11357-1,-2 | 145           |
| C Temperature of deflection under load                                | 1.80 MPa          | °C                  | ISO 75-1,-2    | 125           |
| C Temperature of deflection under load                                | 0.45 MPa          | °C                  | ISO 75-1,-2    | 138           |
| C Vicat softening temperature   | 50 N; 50 °C/h     | °C                  | ISO 306        | 145           |
| Vicat softening temperature   | 50 N; 120 °C/h    | °C                  | ISO 306        | 146           |
| C Coefficient of linear thermal expansion, parallel                   | 23 to 55 °C       | 10 <sup>-4</sup> /K | ISO 11359-1,-2 | 0.65          |
| C Coefficient of linear thermal expansion, normal                     | 23 to 55 °C       | 10 <sup>-4</sup> /K | ISO 11359-1,-2 | 0.65          |
| C Burning behavior UL 94 [UL recognition]                             | 0.75 mm           | Class               | UL 94          | V-2 (CL)      |
| Burning behavior UL 94 [UL recognition]                               | 2.9 mm            | Class               | UL 94          | HB (CL)       |
| C Oxygen index  | Method A          | %                   | ISO 4589-2     | 28            |
| Thermal conductivity, normal  | 23 °C; 50 % r. h. | W/(m·K)             | ISO 8302       | 0.20          |
| Resistance to heat (ball pressure test)                               |                   | °C                  | IEC 60695-10-2 | 136           |
| Relative temperature index (Tensile strength) [UL recognition]        | 1.5 mm            | °C                  | UL 746B        | 125           |
| Relative temperature index (Tensile impact strength) [UL recognition] | 1.5 mm            | °C                  | UL 746B        | 115           |
| Relative temperature index (Electric strength) [UL recognition]       | 1.5 mm            | °C                  | UL 746B        | 125           |
| Glow wire test (GWFI)   | 1.0 mm            | °C                  | IEC 60695-2-12 | 850           |
| Glow wire test (GWFI)   | 1.5 mm            | °C                  | IEC 60695-2-12 | 875           |
| Glow wire test (GWFI)   | 3.0 mm            | °C                  | IEC 60695-2-12 | 930           |
| Glow wire test (GWIT)   | 0.75 mm           | °C                  | IEC 60695-2-13 | 875           |
| Glow wire test (GWIT)   | 1.5 mm            | °C                  | IEC 60695-2-13 | 875           |
| Glow wire test (GWIT)   | 3.0 mm            | °C                  | IEC 60695-2-13 | 900           |
| Burning rate (US-FMVSS)   | ≥1.0 mm           | mm/min              | ISO 3795       | passed        |
| Flash ignition temperature  |                   | °C                  | ASTM D1929     | 480           |
| Self ignition temperature   |                   | °C                  | ASTM D1929     | 550           |
| <b>Electrical properties (23 °C/50 % r. h.)</b>                       |                   |                     |                |               |
| C Relative permittivity   | 100 Hz            | -                   | IEC 60250      | 3.1           |
| C Relative permittivity   | 1 MHz             | -                   | IEC 60250      | 3.0           |
| C Dissipation factor  | 100 Hz            | 10 <sup>-4</sup>    | IEC 60250      | 5             |
| C Dissipation factor  | 1 MHz             | 10 <sup>-4</sup>    | IEC 60250      | 95            |
| C Volume resistivity  |                   | Ohm·m               | IEC 60093      | 1E14          |
| C Surface resistivity   |                   | Ohm                 | IEC 60093      | 1E16          |
| C Electrical strength   | 1 mm              | kV/mm               | IEC 60243-1    | 34            |
| C Comparative tracking index CTI                                      | Solution A        | Rating              | IEC 60112      | 250           |
| Comparative tracking index CTI M                                      | Solution B        | Rating              | IEC 60112      | 125M          |
| <b>Other properties (23 °C)</b>                                       |                   |                     |                |               |
| C Water absorption (saturation value)                                 | Water at 23 °C    | %                   | ISO 62         | 0.30          |
| C Water absorption (equilibrium value)                                | 23 °C; 50 % r. h. | %                   | ISO 62         | 0.12          |
| C Density   |                   | kg/m <sup>3</sup>   | ISO 1183-1     | 1190          |
| Bulk density  | Pellets           | kg/m <sup>3</sup>   | ISO 60         | 660           |
| <b>Material specific properties</b>                                   |                   |                     |                |               |
| Refractive index  | Procedure A       | -                   | ISO 489        | 1.584         |
| Haze for transparent materials  | 3 mm              | %                   | ISO 14782      | < 0.5         |
| Luminous transmittance (clear transparent materials)                  | 1 mm              | %                   | ISO 13468-2    | 90            |
| C Luminous transmittance (clear transparent materials)                | 2 mm              | %                   | ISO 13468-2    | 90            |
| Luminous transmittance (clear transparent materials)                  | 3 mm              | %                   | ISO 13468-2    | > 89          |
| Luminous transmittance (clear transparent materials)                  | 4 mm              | %                   | ISO 13468-2    | > 89          |

# Makrolon® LED5101

| Property  | Test Condition | Unit | Standard | typical Value |
|---|----------------|------|----------|---------------|
| <b>Processing conditions for test specimens</b> |                |      |          |               |
| C Injection molding - Melt temperature          |                | °C   | ISO 294  | 280           |
| C Injection molding - Mold temperature          |                | °C   | ISO 294  | 80            |
| C Injection molding - Injection velocity        |                | mm/s | ISO 294  | 200           |

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break



# Makrolon® LED5101

## Disclaimer

### General

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee, and is subject to change without notice. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. With respect to health, safety and environment precautions, the relevant Material Safety Data Sheets (MSDS) and product labels must be observed prior to working with our products.

---

Covestro AG  
Polycarbonates Business Unit  
Kaiser-Wilhelm-Allee 60  
51373 Leverkusen  
Germany  
plastics@covestro.com  
www.plastics.covestro.com