

NORYL™ RESIN GFN1F

REGION ASIA

DESCRIPTION

NORYL™ GFN1F resin is a 10% glass reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN1F carries a UL746C outdoor suitability rating of F1 along with FDA food contact compliance and NSF 61 listings in several colors. The properties of this material makes it an excellent candidate for water management applications such as water filter and meter components, pump housings / impellers, shower + faucet, and valves.*See NORYL GFN1 resin for NON FDA / NSF version.

TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	75	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	75	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	3.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	4400	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	105	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3400	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.5	%	ISO 527
Tensile Strain, break, 50 mm/min	4.5	%	ISO 527
Tensile Modulus, 1 mm/min	3900	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	115	MPa	ISO 178
Flexural Modulus, 2 mm/min	3700	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	410	J/m	ASTM D 4812
Izod Impact, notched, 23°C	84	J/m	ASTM D 256
Izod Impact, notched, -30°C	80	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	20	J	ASTM D 3763
Izod Impact, unnotched 80°10'4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	30	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	9	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	8	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	135	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	130	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.5E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	129	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	90	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	90	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	90	°C	UL 746B
PHYSICAL			
Specific Gravity	1.17	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.55 – 0.66	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	4	g/10 min	ASTM D 1238
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.12	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	4	cm ³ /10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-228544	-	-
UL Yellow Card Link 2	E45587-237019	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	105 – 110	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	295 – 315	°C	
Front - Zone 3 Temperature	280 – 315	°C	
Middle - Zone 2 Temperature	270 – 310	°C	
Rear - Zone 1 Temperature	260 – 305	°C	
Mold Temperature	75 – 105	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.