

# LNP<sup>TM</sup> LUBRILOY<sup>TM</sup> COMPOUND UA200A

UA

## DESCRIPTION

LNP LUBRILOY\* UA200A is a compound based on Polyphthalamide resin containing Aramid Fiber, Proprietary Lubricant. Added feature of this material is: Wear Resistant.

## TYPICAL PROPERTY VALUES

Revision 20200205

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, break	86	MPa	ASTM D 638
Tensile Strain, break	3.3	%	ASTM D 638
Tensile Modulus, 50 mm/min	4290	MPa	ASTM D 638
Flexural Stress	131	MPa	ASTM D 790
Flexural Modulus	3720	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	603	J/m	ASTM D 4812
Izod Impact, notched, 23°C	32	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	253	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	118	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	5.93E-05	1/°C	ASTM E 831
Thermal Conductivity	0.29	W/m·°C	ASTM E 1530
<b>PHYSICAL</b>			
Density	1.16	g/cm <sup>3</sup>	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.42	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.9 – 1.1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.4 – 1.6	%	ASTM D 955
Wear Factor Washer	5	10 <sup>-10</sup> in <sup>4</sup> ·min/ft·lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.25	-	ASTM D 3702 Modified: Manual
Static COF	0.21	-	ASTM D 3702 Modified: Manual
<b>INJECTION MOLDING</b>			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	310 – 315	°C	
Front - Zone 3 Temperature	305 – 315	°C	
Middle - Zone 2 Temperature	305 – 315	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	120 – 150	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.