

LNPTM THERMOCOMPTM COMPOUND UC006H

UC-1006

DESCRIPTION

LNP THERMOCOMPTM UC006H is a compound based on Polyphthalamide resin containing 30% Carbon Fiber. Added features of this material include: Electrically Conductive, Healthcare.

TYPICAL PROPERTY VALUES

Revision 20201123

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	287	MPa	ASTM D 638
Tensile Strain, break	1.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	26110	MPa	ASTM D 638
Flexural Stress	419	MPa	ASTM D790
Flexural Modulus	22630	MPa	ASTM D790
Tensile Stress, break	263	MPa	ISO 527
Tensile Strain, break	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	28160	MPa	ISO 527
Flexural Stress	413	MPa	ISO 178
Flexural Modulus	22320	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	827	J/m	ASTM D4812
Izod Impact, notched, 23°C	74	J/m	ASTM D 256
Instrumented Dart Impact Energy @ peak, 23°C	8	J	ASTM D3763
Multiaxial Impact	2	J	ISO 6603
Izod Impact, unnotched 80°10°4 +23°C	51	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	285	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	3.96E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.89E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.02E-05	1/°C	ISO 11359-2
PHYSICAL			
Density	1.32	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.31	%	ASTM D570
Mold Shrinkage, flow, 24 hrs	0.2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs	0.6	%	ASTM D955
Mold Shrinkage, flow, 24 hrs	0.16	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.62	%	ISO 294
Wear Factor Washer	6	10 ⁻¹⁰ in ¹⁵ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.27	-	ASTM D 3702 Modified: Manual
Static COF	0.21	-	ASTM D 3702 Modified: Manual
Density	1.32	g/cm ³	ISO 1183

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.66	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	315 – 330	°C	
Front - Zone 3 Temperature	325 – 340	°C	
Middle - Zone 2 Temperature	315 – 325	°C	
Rear - Zone 1 Temperature	310 – 320	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.