

LX-7603

Polycarbonate compound resin

General Information

Description

High impact strength
Non-brominated, non-chlorinated flame retardant
Diffusion plate, diffusion profile and finishing materials

Applications

Light Diffusion Grade

Typical properties¹

	Test Method	Typical value	Unit
Physical			
Melt Flow Index, 300 °C, 1.2kg	ASTM D1238	-	g/10min
Specific Gravity	ASTM D792	1.2	
Mold Shrinkage	HPC method	0.5-0.7	%
Mechanical			
Tensile Strength, yield, 50mm/min	ASTM D638	610	kgf/cm ²
Tensile Elongation, break, 50mm/min	ASTM D638	>100	%
Flexural Strength, yield, 10mm/min	ASTM D790	890	kgf/cm ²
Flexural Modulus, 10mm/min	ASTM D790	23,000	kgf/cm ²
IZOD Impact Strength, notched, 23 °C, 1/8"	ASTM D256	75	kg-cm/cm
	ASTM D256	-	kg-cm/cm
	ASTM D256	-	kg-cm/cm
Thermal			
Heat Distortion Temp. 4.6kgf/cm ²	ASTM D648	-	°C
	ASTM D648	129	°C
Vicat Softening Temp. Rate B/50	ASTM D1525	-	°C
Flammability			
UL94 V-0	UL94	1.5	Mm
Optical Properties			
Light transmittance	ASTM D1003	70	%

Notes

ISO 9001, 14001, /TS 16949


¹ Typical properties : these are not to be construed as specifications.

LX-7603

Polycarbonate compound resin

Processing guides¹

	Typical value	Unit	
Drying condition			
Drying temperature	120	°C	
Drying time	4	hr	
Maximum moisture content	0.02	%	
Injection molding			
Melt temperature	290 ~ 310	°C	
Nozzle temperature	280 ~ 300	°C	
Barrel	Rear zone	290 ~ 310	°C
	Middle zone	280 ~ 300	°C
	Front zone	270 ~ 290	°C
Hopper temperature	60 ~ 80	°C	
Mold temperature	60 ~ 90	°C	



Recycling

Sprues and runners can be reground with virgin resin within the ratio of 5%. Care must be taken to ensure that the regrind is free from impurities and regrind should not be used in applications where impact performance and/or agency compliance are required.

Notes

ISO 9001, 14001, /TS 16949

¹ Processing guides : Typical processing parameters are noted. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, etc.